

Technical Information

Rev. 6, June 2007



Kalrez[®] perfluoroelastomer
parts

From DuPont Performance Elastomers

Kalrez[®] Sahara[™] 8085

Product Description

Kalrez[®] Sahara[™] 8085 is a beige, general purpose product for all plasma process applications, i.e., etching, ashing/stripping, HDPCVD, PECVD, SACVD, etc. It has been formulated for minimal particle generation in NF₃ plasma. Kalrez[®] Sahara[™] 8085 exhibits very low particle generation and low weight loss in oxygen and fluorine-based plasmas, has excellent mechanical properties and is well-suited for both static and dynamic sealing applications (e.g., bonded slit valve doors, bonded gate valves, bonded pendulum valves, gas orifice seals, gas feedthrough seals, chamber lid seals, etc.) A maximum continuous service temperature of 240°C is suggested. Kalrez[®] Sahara[™] 8085 can also withstand short-term excursions up to 275°C. Ultrapure post-cleaning and packaging is standard for parts made from Kalrez[®] Sahara[™] 8085.

Performance Features/Benefits

- Very low particle generation in NF₃ plasma
- Longer seal life
- Reduced PM time and increased equipment uptime
- Lower cost of ownership

Suggested Applications

- Bonded slit valve door seals
- Bonded gate valves
- Chamber lid seals
- Gas inlet seals
- Gas orifice seals
- Gas feedthrough seals

Typical Physical Properties¹

Color	Beige
Hardness, Shore A (pellet) ²	80
Hardness, Shore M (O-ring) ³	86
100% Modulus ⁴ , MPa	7.5
Tensile Strength at Break ⁴ , MPa	16.3
Elongation at Break ⁴ , %	159
Compression Set ⁵ , %	
70 hr at 150°C	28
70 hr at 175°C	35
70 hr at 204°C	42
Max. Continuous Service Temperature ⁶ , °C	240
Max. Excursion Temperature ⁶ , °C	275

¹ Not to be used for specification purposes

² ASTM D2240 (pellet test specimens)

³ ASTM D2240 and ASTM D1414 (AS568 K214 O-ring test specimens)

⁴ ASTM D412 (dumbbell test specimens)

⁵ ASTM D395B and ASTM D1414 (AS568 K214 O-ring test specimens)


⁶ DuPont Performance Elastomers proprietary test methods

Fabs Choose Kalrez[®] Sahara[™] 8085 For Improved Performance

Kalrez[®] Sahara[™] 8085 has been reported to significantly improve wafer production in a variety of semiconductor plasma process applications, i.e., etching, ashing/stripping, HDPCVD, PECVD, SACVD, etc., where oxygen and fluorinated plasmas are used during the cleaning cycle. In a number of evaluations at fabline customers, Kalrez[®] Sahara[™] 8085 exhibited improved mechanical strength, lower particle generation and longer seal life compared to competitive perfluoroelastomers in both static and dynamic sealing applications.

Case Report #3137—Kalrez® Sahara™ 8085 Reported to Reduce Particle Adders by 53% Over Competitive Perfluoroelastomer (FFKM A11)

- HDPCVD O-ring
- Process chemistry: Silane
- Cleaning chemistry: NF_3 , O_2 and O_3
- Competitive FFKM generated significantly more particle adders



Case Report #4115 – Kalrez® Sahara™ 8085 Extended Seal Life 100% Versus Competitive Perfluoroelastomer (FFKM A18)

- PECVD RPS cleaning module O-ring seals
- Process chemistry: SiH_4 , O_2
- Cleaning chemistry: NF_3
- Competitive perfluoroelastomer failed due to severe plasma attack, i.e., erosion, cracking, etc.

Case Report #6553 — Kalrez® Sahara™ 8085 Improved Wafer Production over 25% versus Competitive Perfluoroelastomer (FFKM A2)

- PECVD gas box, shower head and plate seal
- Process chemistry: TEOS, O_2 at 400°C
- Cleaning chemistry: NF_3 plasma at 3500 watts
- Competitive perfluoroelastomer failed due to cracking and excessive leakage

Case Report #2883 — Kalrez® Sahara™ 8085 Extended Seal Life 100% Versus Competitive Perfluoroelastomer (FFKM A2)

- Ash isolation valve poppet seal
- Process chemistry: O_2 , CF_4
- Cleaning chemistry: N/A
- Competitive perfluoroelastomer failed due to cracking and excessive leakage

For further information please contact one of the offices below, or visit our website at www.dupontelastomers.com/kalrez

Global Headquarters – Wilmington, DE USA

Tel. +1-800-853-5515
+1-302-792-4000
Fax +1-302-792-4450

European Headquarters - Geneva

Tel. +41-22-717-4000
Fax +41-22-717-4001

South & Central America Headquarters - Brazil

Tel. +55-11-4166-8978
Fax +55-11-4166-8989

Asia Pacific Headquarters - Singapore

Tel. +65-6275-9383
Fax +65-6275-9395

Japan Headquarters – Tokyo

Tel. +81-3-6402-6300
Fax. +81-3-6402-6301

The information set forth herein is furnished free of charge and is based on technical data that DuPont Performance Elastomers believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont Performance Elastomers customer service representative and read Medical Caution Statement H-69237.

DuPont is a trademark of DuPont and its affiliates.

Kalrez® and Kalrez® Sahara™ are trademarks or registered trademarks of DuPont Performance Elastomers.
Copyright © 2007 DuPont Performance Elastomers. All Rights Reserved.