

DuPont™ Kalrez® 8575

Technical Information — September 2010

Product Description

DuPont™ Kalrez® 8575 perfluoroelastomer parts are a white product for “select” etching, ashing/stripping and deposition process applications. It offers low weight loss in Oxygen and Fluorine-Based Plasmas, low outgassing and excellent elastic recovery properties. Kalrez® Sahara™ 8575 has excellent vacuum and long-term sealing performance, good mechanical properties and is well-suited for both static and dynamic sealing applications (e.g., gas inlets, chamber lid seals, slit valve door seals, etc.). A maximum continuous service temperature of 300°C (572°F) is suggested. Ultrapure Post-Cleaning and Packaging is standard for all parts made from Kalrez® Sahara™ 8575.

Typical Physical Properties¹

Color	White
Maximum Application Temperature ² , °C (°F)	300 (572)
Maximum Application Pressure ² , MPa (psi)	3.45 (500)
Durometer, Shore A ³	62
Durometer, Shore M (o-ring)	72
100% Modulus ⁴ , MPa (psi)	2.47 (360)
Elongation at break ⁴ , %	230
Tensile at break ⁴ , MPa (psi)	12.04 (1750)
Compression set ⁵ , % (70 hours at 204°C (400°F))	
Pellet	29
Size 214 O-Ring	17
Specific Gravity, g/cc	2.26

¹Not to be used for specification

²DuPont proprietary test method – maximum application temperature and pressure may vary with seal design and application specifics

³ASTM D2240 (pellet test specimen)

⁴ASTM D412, 500mm/min

⁵ASTM D395B



The miracles of science™

Additional Physical Properties¹

Tg ² , °C (°F)	
TR-10 ³ , °C (°F)	-3 (26)
Brittle Point ⁴ , °C (°F)	
Linear Coefficient of Thermal Expansion, /°C (/°F)	2.85x10 ⁻⁴ (1.58x10 ⁻⁴)
Abrasion Resistance ⁵ , (volume loss, cubic mm)	148.8
Coefficient of friction ⁶ (to steel)	
Static	1.04
Dynamic	0.624
Volume resistivity ⁷ , ohms/square	4.42 x 10E+16
Surface resistivity ⁷ , Ohm-cm	1.72 x 10E+16
Dielectric Constant ⁸ at 150°C and 1 MHz	2.707
Dissipation Factor ⁸ at 150°C and 1MHz	0.0007

¹Not to be used for specification

²DuPont proprietary test method – maximum application temperature and pressure may vary with seal design and application specifics

³ASTM D1329

⁴ASTM D746

⁵Din 53 516

⁶ASTM 1894

⁷ASTM D 257

⁸ASTM D150

Visit us at kalrez.dupont.com or vespel.dupont.com

Contact DuPont at the following regional locations:

North America
800-222-8377

Latin America
+0800 17 17 15

Europe, Middle East, Africa
+41 22 717 51 11

Greater China
+86-400-8851-888

ASEAN
+65-6586-3688

Japan
+81-3-5521-8484

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer service representative and read Medical Caution Statement H-50103-3.

Copyright © 2010 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, Kalrez®, and Vespel® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

Kalrez® Application Guide – September 2010



The miracles of science™